

www.prolightopto.com





ProLight PK2N-1JJE-A 1W Infrared 850 Power LED Technical Datasheet Version: 1.3

# **ProLight Opto PK2N Series**

### Features

- $\cdot$  Viewing angle: 45°
- · Instant light (less than 100ns)
- $\cdot$  Lead free reflow soldering
- · RoHS compliant
- $\cdot$  Cool beam, safe to the touch
- · Superior ESD protection

### **Main Applications**

- · Surveillance
- · Gesture recognition
- $\cdot$  In-cabin automotive device

### Introduction


•ProLight PK2N-1JJE-A-viewing angle 45°, is one of the smallest high power LED footprint available by ProLight Opto, has offered extended solid-state lighting design possibilities. ProLight PK2N-1JJE-A-viewing angle 45° is designed with ProLight own Patents and using copper leadframe, the best thermal material of the world.

•PK2N-1JJE-A-viewing angle 45° qualifies as the JEDEC Level 1 MSL sensitivity level and suitable for SMD process, Pb\_free reflow soldering capability, and full compliance with EU Reduction of Hazardous Substances (RoHS) legislation.


#### ProLight Opto Technology Corp.



### **Emitter Mechanical Dimensions**



Circuit Diagram



Notes:

- 1. The cathode side of the device is denoted by the chamfer on the part body.
- 2. Electrical insulation between the case and the board is required. Do not electrically connect either the anode or cathode to the slug.
- 3. Drawing not to scale.
- 4. All dimensions are in millimeters.
- 5. Unless otherwise indicated, tolerances are  $\pm$  0.10mm.
- 6. Please do not solder the emitter by manual hand soldering, otherwise it will damage the emitter.
- 7. Please do not use a force of over 0.3kgf impact or pressure on the lens of the LED, otherwise it will cause a catastrophic failure.

\*The appearance and specifications of the product may be modified for improvement without notice.

#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)



## Flux Characteristics, $T_J = 25^{\circ}C$

Part Number	Radiant Inten	sity I <sub>e</sub> (mW/sr)	Radiometric Power (mW)	
Emitter	@70	0mA	Refer @700mA	Refer @350mA
	Min.	Тур.	Тур.	Тур.
PK2N-1JJE-A	400	530	500	270

• ProLight maintains a tolerance of ± 7% on flux and power measurements.

• Please do not drive at rated current more than 1 second without proper heat sink.

### Electrical Characteristics at 700mA, $T_1 = 25^{\circ}C$

	Fo	rward Voltage V <sub>F</sub>	Thermal Resistance	
Color	Min.	Тур.	Max.	Junction to Slug (°C/W)
Infrared 850	1.3	1.7	2.0	10

• ProLight maintains a tolerance of  $\pm$  0.1V for Voltage measurements.

### Optical Characteristics at 700mA, $T_1 = 25^{\circ}C$

				Total	
				included	Viewing
				Angle	Angle
Color	Peak Wavelength $\lambda_P$		λ <sub>P</sub>	(degrees)	(degrees)
COIOI	Min.	Тур.	Max.	θ <sub>0.90V</sub>	<b>2 θ</b> <sub>1/2</sub>
Infrared 850	840 nm	855 nm	870 nm	125	45

• ProLight maintains a tolerance of ± 1nm for dominant wavelength measurements.

#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)



### **Absolute Maximum Ratings**

Parameter	Infrared 850	
DC Forward Current (mA)	700	
Peak Pulsed Forward Current (mA)	1000 (less than 1/10 duty cycle@1KHz)	
ESD Sensitivity (HBM per MIL-STD-883E Method 3015.7)	±4000V (Class III)	
LED Junction Temperature	120°C	
Operating Board Temperature at Maximum DC Forward Current	-40°C - 90°C	
Storage Temperature	-40°C - 120°C	
Soldering Temperature	JEDEC 020c 260°C	
Allowable Reflow Cycles	3	
Reverse Voltage	Not designed to be driven in reverse bias	

### **Radiometric Power Bin Structure**

Color	Bin Code	Minimum Radiant Intensity I <sub>e</sub> (mW/sr)	Maximum Radiant Intensity I <sub>e</sub> (mW/sr)	Available Color Bins
Infrared 850	G	400	500	All
	H	500	630	[1]

• ProLight maintains a tolerance of ± 7% on flux and power measurements.

• The flux bin of the product may be modified for improvement without notice.

• <sup>[1]</sup> The rest of color bins are not 100% ready for order currently. Please ask for quote and order possibility.

### **Peak Wavelength Bin Structure**

Color	Bin Code	Minimum Peak Wavelength (nm)	Maximum Peak Wavelength (nm)
Infrared 850	] 1	840	870

• ProLight maintains a tolerance of ± 1nm for peak wavelength measurements.

ProLight Opto Technology Corp.


No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)

Tel : +886-3-461-8618 Fax : +886-3-461-8677




### Color Spectrum, T<sub>J</sub> = 25°C

1. Infrared 850



### **Light Output Characteristics**

Relative Light Output vs. Junction Temperature at 700mA




#### ProLight Opto Technology Corp.

2022/09 | DS-1370




### Forward Current Characteristics, T<sub>J</sub> = 25°C



### **Ambient Temperature vs. Maximum Forward Current**


1. Infrared 850 (T<sub>JMAX</sub> = 120°C)



#### ProLight Opto Technology Corp.



### **Typical Representative Spatial Radiation Pattern**



#### ProLight Opto Technology Corp.



### **Qualification Reliability Testing**

Stress Test	Stress Conditions	Stress Duration	Failure Criteria
Room Temperature Operating Life (RTOL)	25°C, I <sub>F</sub> = max DC (Note 1)	1000 hours	Note 2
Wet High Temperature Operating Life (WHTOL)	85°C/60%RH, I <sub>F</sub> = max DC (Note 1)	1000 hours	Note 2
Wet High Temperature Storage Life (WHTSL)	85°C/85%RH, non-operating	1000 hours	Note 2
High Temperature Storage Life (HTSL)	110°C, non-operating	1000 hours	Note 2
Low Temperature Storage Life (LTSL)	-40°C, non-operating	1000 hours	Note 2
Non-operating Temperature Cycle (TMCL)	-40°C to 120°C, 30 min. dwell, <5 min. transfer	200 cycles	Note 2
Mechanical Shock	1500 G, 0.5 msec. pulse, 5 shocks each 6 axis		Note 3
Natural Drop	On concrete from 1.2 m, 3X		Note 3
Variable Vibration Frequency	10-2000-10 Hz, log or linear sweep rate, 20 G about 1 min., 1.5 mm, 3X/axis		Note 3
Solder Heat Resistance (SHR)	260°C ± 5°C, 10 sec.		Note 3
Solderability	Steam age for 16 hrs., then solder dip at 260°C for 5 sec.		Solder coverage on lead

Notes:

1. Depending on the maximum derating curve.

2. Criteria for judging failure

Item	Test Condition	Criteria for Judgement		
liem	Test Condition	Min.	Max.	
Forward Voltage (V <sub>F</sub> )	I <sub>F</sub> = max DC		Initial Level x 1.1	
Luminous Flux or Radiometric Power ( $\Phi_V$ )	I <sub>F</sub> = max DC	Initial Level x 0.7		
Reverse Current (I <sub>R</sub> )	$V_R = 5V$		50 µA	

\* The test is performed after the LED is cooled down to the room temperature.

3. A failure is an LED that is open or shorted.


#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)



### **Recommended Solder Pad Design**

**Standard Emitter** 



- All dimensions are in millimeters.
- Electrical isolation is required between Slug and Solder Pad.

#### ProLight Opto Technology Corp.


No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)

Tel : +886-3-461-8618 Fax : +886-3-461-8677



### **Reflow Soldering Condition**

Profile Feature	Sn-Pb Eutectic Assembly	Pb-Free Assembly	
Average Ramp-Up Rate	3°C / second max.	3°C / second max.	
(T <sub>Smax</sub> to T <sub>P</sub> )	5 C/ Second max.	S C / Second max.	
Preheat			
– Temperature Min (T <sub>Smin</sub> )	100°C	150°C	
– Temperature Max (T <sub>smax</sub> )	150°C	200°C	
– Time (t <sub>smin</sub> to t <sub>smax</sub> )	60-120 seconds	60-180 seconds	
Time maintained above:			
– Temperature (T <sub>L</sub> )	183°C	217°C	
– Time (t <sub>l</sub> )	60-150 seconds	60-150 seconds	
Peak/Classification Temperature (T <sub>p</sub> )	240°C	260°C	
Time Within 5°C of Actual Peak	10-30 seconds	20-40 seconds	
Temperature (t <sub>p</sub> )	TO-20 Seconds	20-40 seconds	
Ramp-Down Rate	6°C/second max.	6°C/second max.	
Time 25°C to Peak Temperature	6 minutes max.	8 minutes max.	




- We recommend using the M705-S101-S4 solder paste from SMIC (Senju Metal Industry Co., Ltd.) for lead-free soldering.
- Do not use solder pastes with post reflow flux residue>47%. (58Bi-42Sn eutectic alloy, etc) This kind of solder pastes may cause a reliability problem to LED.
- All temperatures refer to topside of the package, measured on the package body surface.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a double-head soldering iron should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- Reflow soldering should not be done more than three times.
- When soldering, do not put stress on the LEDs during heating.
- After soldering, do not warp the circuit board.

#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)



### **Emitter Reel Packaging**



Notes:


- 1. Drawing not to scale.
- 2. All dimensions are in millimeters.
- 3. Unless otherwise indicated, tolerances are  $\pm$  0.10mm.

#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)



### **Emitter Reel Packaging**



Notes:

- 1. Empty component pockets sealed with top cover tape.
- 2. 500 pieces per reel.
- 3. Drawing not to scale.
- 4. All dimensions are in millimeters.

#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)

Tel : +886-3-461-8618 Fax : +886-3-461-8677



### **Precaution for Use**

Storage

Please do not open the moisture barrier bag (MBB) more than one week. This may cause the leads of LED discoloration. We recommend storing ProLight's LEDs in a dry box after opening the MBB. The recommended storage conditions are temperature 5 to 30 °C and humidity less than 40% RH. It is also recommended to return the LEDs to the MBB and to reseal the MBB.

- The slug is is not electrically neutral. Therefore, we recommend to isolate the heat sink.
- We recommend using the M705-S101-S4 solder paste from SMIC (Senju Metal Industry Co., Ltd.) for lead-free soldering.
- Do not use solder pastes with post reflow flux residue>47%. (58Bi-42Sn eutectic alloy, etc) This kind of solder pastes may cause a reliability problem to LED.
- Any mechanical force or any excess vibration shall not be accepted to apply during cooling process to normal temperature after soldering.
- Please avoid rapid cooling after soldering.
- Components should not be mounted on warped direction of PCB.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a heat plate should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- This device should not be used in any type of fluid such as water, oil, organic solvent and etc. When cleaning is required, isopropyl alcohol should be used.
- When the LEDs are illuminating, operating current should be decide after considering the package maximum temperature.
- The appearance, specifications and flux bin of the product may be modified for improvement without notice. Please refer to the below website for the latest datasheets. <u>http://www.prolightopto.com/</u>

### **Handling of Silicone Lens LEDs**

Notes for handling of silicone lens LEDs

- Please do not use a force of over 0.3kgf impact or pressure on the silicone lens, otherwise it will cause a catastrophic failure.
- The LEDs should only be picked up by making contact with the sides of the LED body.
- Avoid touching the silicone lens especially by sharp tools such as Tweezers.
- Avoid leaving fingerprints on the silicone lens.
- Please store the LEDs away from dusty areas or seal the product against dust.
- When populating boards in SMT production, there are basically no restrictions regarding the form of the pick and place nozzle, except that mechanical pressure on the silicone lens must be prevented.
- Please do not mold over the silicone lens with another resin. (epoxy, urethane, etc)





#### ProLight Opto Technology Corp.

No. 89, Xiyuan Rd., Zhongli Dist., Taoyuan City 32057, Taiwan (R.O.C.)

#### 13